



Received: 02/21/2014 Completed: 02/27/2014 Letter: I RR P.O.#: Test Report #: 3-00852-0-

Client's Identification Style: Wyndham Lot 367929-Piece #: 367919-3. Content: 100% Polyester. Width: 64.5". Weight: 6.7 oz. End Use: Table Skirts

Key Test: NFPA 701-2010 TM#1

Tel: 1-(972)-466-1030

Ext: 117

Fax: 1-(972)-236-6103

PC: 0.5H DL/jd

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2010 Edition - Test Method #1

PRODUCT CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

RESULTS REPORTED: ☒ Initially; ☐ After 3 dry cleanings; ☐ After 5 launderings @ 160°F

RESULTS:

Specimen #	Afterflame* (seconds)	Flaming Drip (seconds)	Weight Loss (percent)
1	0	0	19.4
2	0	0	1.6
3	0	0	16.7
4	0	0	33.3
5	0	0	8.3
6	0	0	32.8
7	0	0	36.1
8	0	0	26.7
9	0	0	17.7
10	0	0	27.4
Mean:		0	Mean: 22.0

STATISTICAL VALUES: SD = 11.3 3 SD = 33.9 Mean + 3 SD = 55.9

ABBREVIATIONS USED: SD = Standard deviation. NT = Not tested.

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 204 g/m²

PRECONDITIONING: ☒ 0.5 hr @ 220°F (Standard)
☐ 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

CONVERSION FACTOR: g/m² ÷ 28.35 x .835 = oz/yd²

NOTE:

1. All specimens prepared in the length direction.
2. See addendum for individual specimen weights.



The
Govmark
Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 2

Received: 02/21/2014 Completed: 02/27/2014 Letter: I RR P.O.#: Test Report #: 3-00852-0-

Client's Identification Style: Wyndham Lot 367929-Piece #: 367919-3. Content: 100% Polyester. Width: 64.5". Weight: 6.7 oz. End Use: Table Skirts

Key Test: NFPA 701-2010 TM#1

Tel: 1-(972)-466-1030 Ext: 117
Fax: 1-(972)-236-6103

REMARKS:

- ☒ Flames did not project above the top of the specimen.
☐ Flames projected above the top of the specimen; Specimen #'s _____
☐ Other: _____

FAILURE CRITERIA: As cited by NFPA 701 - 2010 Edition Test Method #1

Afterflame	Flaming Drip (Mean)	Weight Loss (percent)	
		Mean	Individual Specimen
*	Exceeds 2 seconds	Exceeds 40%	Exceeds Mean + 3 SD**


CONCLUSION: Based on the Results on page 1 and the above Failure Criteria cited by NFPA 701 - 2010 Edition Test Method #1, the item tested:

- ☒ Passes; ☐ Fails; ☐ Requires testing of 10 additional specimens
i.e. only one individual specimen failure was noted

* Afterflame is required to be recorded; however, the NFPA document does not factor it into the Failure Criteria reporting requirements. It should be noted that excessive afterflames (15 seconds or more) could be cause for rejection by local fire authorities performing "match" field tests.

** See "Discussion" on Page 3.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #1.



AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /je/ljb
MS. PHYLLIS PETTIT

MAR 04 2014